



Product Data Sheet

FilmTec™ Fortilife™ XC80 Element

Push TDS Limit and Maximize Water Recovery in Brine Concentration

Description

The FilmTec™ Fortilife™ product line offers industrial users a reliable and highly efficient option to help solve their most difficult water challenges, such as wastewater reuse and Minimal Liquid Discharge (MLD).

Key benefits of the FilmTec™ Fortilife™ XC80 Element include:

- The ability to achieve reject Total Dissolved Solids (TDS) level > 80,000 ppm within standard reverse osmosis (RO) operating limits, helping lower brine volume and maximize water recovery in the brine concentration step
- Improved cost-efficiency of the overall MLD or Zero Liquid Discharge (ZLD) system due to brine reduction to downstream thermal treatment
- Lower reverse osmosis (RO) energy consumption
- Slower permeate flow rate decline enabled by a highly fouling-resistant membrane
- Robust membrane and reliable long-term performance
- The wide pH range for cleanings (pH 1 – 13) allows effective cleaning in severe fouling
- Support from highly specialized and experienced technical experts

These industry-leading benefits result from a distinct combination of:

- A highly permeable, fouling resistant membrane
- An oxidative-free membrane manufacturing process

Product Type

Spiral-wound element with polyamide thin-film composite membrane

Exemplary Brine Concentration Projections

	P_f (bar)	Feed TDS (ppm)	Concentrate TDS (ppm)	Ave Op. flux (LMH)	Recovery (%)
FilmTec™ Element					
Fortilife™ XC80	70	60,000	77,000	13	23


1. Results in the table are based from a ROSA simulation of a single 3 element pressure vessel operated at 25 C, pH 8, feed flow = 7 m³/h and a FF = 0.85, with 60,000ppm NaCl feed.
2. No warranty is provided for the application of this information since use conditions and applicable laws may differ from one location to another and may change with time.

Typical Properties

FilmTec™ Element	Active Area		Feed Spacer	Permeate Flow Rate		Typical Stabilized Salt	Minimum Salt
	(ft ²)	(m ²)	Thickness (mil)	(GPD)	(m ³ /d)	Rejection (%)	Rejection (%)
Fortilife™ XC80	440	41	28	9,050	34.2	99.47	99.25

- The above values are based on the following testing conditions: 32,000 ppm NaCl, 600 psi (4.1 MPa), 77°F (25°C), pH 8, 8% recovery.
- Flow rates for individual elements may vary but will be no more than ± 15%.
- Sales specifications may vary as design revisions take place.
- Active area guaranteed ± 3%. Active area as stated by DuPont Water Solutions is not comparable to nominal membrane area often stated by some manufacturers.

Element Dimensions



FilmTec™ Element	Dimensions – inches (mm)				1 inch = 25.4 mm	
	A		B		C	
	(in.)	(mm)	(in.)	(mm)	(in.)	(mm)
Fortilife™ XC80	40.0	1,106	1.125 ID	29 ID	7.9	201

- Refer to [FilmTec™ Design Guidelines for multiple-element systems of 8-inch elements](#) (Form No. 45-D01695-en).
- Element to fit nominal 8-inch (203-mm) I.D. pressure vessel.

Operating and Cleaning Limits

Maximum Operating Temperature ^a	113°F (45°C)
Maximum Operating Pressure ^b	1,200 psig (83 bar)
Maximum Element Pressure Drop	15 psig (1.0 bar)
pH Range	
Continuous Operation ^a	2 – 11
Short-Term Cleaning (30 min.) ^c	1 – 13
Maximum Feed Silt Density Index (SDI)	SDI 5
Free Chlorine Tolerance ^d	< 0.1 ppm

- Maximum temperature for continuous operation above pH 10 is 95°F (35°C).
- Maximum pressure at 25 C. Consult tech service specialist for limits at high temperature.
- Refer to guidelines in [Cleaning Guidelines](#) (Form No. 45-D01696-en) for more information.
- Under certain conditions, the presence of free chlorine and other oxidizing agents will cause premature membrane failure. Since oxidation damage is not covered under warranty, DuPont Water Solutions recommends removing residual free chlorine by pretreatment prior to membrane exposure. Please refer to [Dechlorinating Feedwater](#) (Form No. 45-D01569-en) for more information.

Additional Important Information

Before use or storage, review these additional resources for important information:

- [Usage Guidelines for FilmTec™ 8" Elements](#) (Form No. 45-D01706-en)
- [Start-Up Sequence](#) (Form No. 45-D01609-en)
- [Storage and Shipping of New FilmTec™ Elements](#) (Form No. 45-D01633-en)

Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- The use of this product in and of itself does not necessarily guarantee the removal of cysts and pathogens from water. Effective cyst and pathogen reduction is dependent on the complete system design and on the operation and maintenance of the system.

Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours Inc. unless otherwise noted. © 2020 DuPont.

